



Material - MSZ 1.4408

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - MSZ 1.4408 Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|--|--|
| Carbon | C % | 0.070 max. | Normalizing or Quenching or Solution Annealing | |
| Silicon | Si % | 1.500 max. | | |
| Manganese | Mn % | 1.500 max. | | |
| Phosphorus | P % | 0.040 max. | | |
| Sulphur | S % | 0.030 max. | | |
| Chromium | Cr % | 18.000 - 20.000 | | |
| Molybdenum | Mo % | 2.000 - 2.500 | | |
| Nickel | Ni % | 9.000 - 12.000 | | |
| Copper | Cu % | 0.500 max. | | |
| Iron | Fe % | Balance | | |
| - | - | - | Mechanical Properties Tensile Strength in Mpa 440 - 640 Yield Strength in Mpa 185 min. Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 60 J @ RT | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |

| Cross Reference Table | | | |
|-----------------------|----------|----------------|------------------------------|
| Material | Standard | Country | Grade Belong to the Industry |
| GX5CrNiMoNb19-11-2 | BS | British | Plate, Tubes and Forging |
| GX5CrNiMoNb19-11-2 | EN | European Union | Casting |
| 1.4408 | EN | European Union | Casting |
| GX5CrNiMoNb19-11-2 | CSN | Czech Republic | Casting |
| 1.4408 | CSN | Czech Republic | Casting |
| GX5CrNiMoNb19-11-2 | MSZ | Hungary | Casting |
| GX5CrNiMoNb19-11-2 | DIN | Germany | Casting |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.