



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - MSZ AH 60

Standard Specification for Alloy Steel Casting

Group - Ferrous Mild Steel Alloys

Sub Group - MSZ AH 60 Alloy Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.150 - 0.400		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	0.300 max.		
Nickel	Ni %	1.500 - 2.200		
Vanadium	V %	0.050 - 0.150		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
24 Ni 8	DIN	Germany	Steel
G 9 Ni 10	EN	European Union	Casting
SCPL 21	JIS	Japan	Casting
G9Ni10	UNS	USA	Casting
J22501	MSZ	Hungary	Casting
A757 B2N B2Q	ASTM	USA	Casting
20 N 8	AFNOR NF	France	Steel

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS