



Material - NBN 1.4308

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - NBN 1.4308 Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.070 max.	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	8.000 - 11.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 - 640
-	-	-	Yield Strength in Mpa	200 min.
-	-	-	Elongation in %	30 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
304C15	BS	British	Casting
304C15LT196	BS	British	Casting
2074/H5A	AS	Australia	Casting
2074/H5AM	AS	Australia	Casting
Z 6 CN 18-10 M	AFNOR NF	France	Casting
1.4308	SFS	Finland	Casting
1.4308	DIN	Germany	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.