



Material - NBN 35 NiCr 6

Standard Specification for Mild Steel Alloys Bar and Rod

Group - Ferrous Mild Steel Alloys

Sub Group - NBN 35 NiCr 6 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.370	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	0.800 - 1.100		
Nickel	Ni %	1.200 - 1.600		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 780 - 1100 Yield Strength in Mpa 640 min. Elongation in % 12 min. Reduction of Area in % 40 min. Hardness in BHN 223 max. Impact in Joule 35 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
35NiCr6	EN	European Union	Bar and Rod
1.5815	EN	European Union	Bar and Rod
1.5815	ONORM	Australia	Bar and Rod
35 NiCr 6	ONORM	Australia	Bar and Rod
1.5815	NBN	Belgium	Bar and Rod
1.5815	BDS	Bulgaria	Bar and Rod
35 NiCr 6	BDS	Bulgaria	Bar and Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.