



Material - NBN GP 280 GH

Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - NBN GP 280 GH Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 - 0.250	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.800 - 1.200		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 max.		
Nickel	Ni %	0.400 max.		
Molybdenum	Mo %	0.120 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.030 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 480 - 640 Yield Strength in Mpa 280 min. Elongation in % 22 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AL2	BS	British	Casting
AL3	BS	British	Casting
UC 14	ONORM	Australia	Wire and Rod
1.0625	ONORM	Australia	Casting
GP 280 GH	ONORM	Australia	Casting
1.0625	NBN	Belgium	Casting
1.0625	BDS	Bulgaria	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.