



Material - NBR CA-6N

Standard Specification for Alloy Steel Casting

Group - Ferrous Stainless Steel Alloys

Sub Group - NBR CA-6N Alloy Steel Casting

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.060 max.	Heating + Reheating + Aging	
Silicon	Si %	1.000 max.		
Manganese	Mn %	0.500 max.		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	10.500 -12.500		
Nickel	Ni %	6.000 - 8.000		
Iron	Fe %	Balance		
-	-	-		
Mechanical Properties				
Tensile Strength in Mpa		965 min.		
Yield Strength in Mpa		930 min.		
Elongation in %		15 min.		
Reduction of Area in %		50 min.		
Hardness in BHN		-		
Impact in Joule		-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A743 CA6N	ASTM	USA	Casting
J91650	UNS	USA	Casting
CA-6N	NMX	Maxicon	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.