



## **Material - ONORM Grade E75**

## Standard Specification for Steel Pipe and Tube for General Engineering Purposes

**Group - Ferrous Mild Steel Alloys** 

Sub Group - ONORM Grade E75 Steel Pipe and Tube for General Engineering Purposes
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Pipe and Tube

Chemical Composition			Heat Treatment	
Phosphorus	P %	0.030 max.	As Raw or Annealing or Normalizing or Hardening and Tempering	
Sulphur	S %	0.030 max.		
Iron	Fe %	Balance		
-	-			
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	1	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	689 min.
-	-	-	Yield Strength in Mpa	517 - 724
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impac <mark>t in Joule</mark>	30 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
BT3	BS	British	Pipe and Tube	
Grade E75	BS	British	Pipe and Tube	
H40	BS	British	Pipe and Tube	
H40	ONORM	Australia	Pipe and Tube	
Grade E75	BDS	Bulgaria	Pipe	
H40	BDS	Bulgaria	Pipe and Tube	
H40	CSN	Czech Republic	Pipe and Tube	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.