

Material - ONORM X 6 CrNiMoNb 17 12 2 KKW

Standard Specification for Seemless Steel Tubes for Pressure Purposes

Group - Ferrous Stainless Steel Alloys

Sub Group - ONORM X 6 CrNiMoNb 17 12 2 KKW Seemless Steel Tubes for Pressure Purposes Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|-------------------------------|-----------|
| Carbon | C % | 0.080 max. | | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 2.000 max. | | |
| Phosphorus | P % | 0.045 max. | Solution Annealing | |
| Sulphur | S % | 0.030 max. | | |
| Chromium | Cr % | 16.500 - 18.500 | | |
| Molybdenum | Mo % | 2.000 - 2.500 | | |
| Nickel | Ni % | 10.500 - 13.500 | | |
| Niobium | Nb % | 1.000 max. | Mechanical Properties | |
| Iron | Fe % | Balance | Tensile Strength in Mpa | 510 - 740 |
| - | - | - | Yield Strength in Mpa | 215 min. |
| - | - | - | Elongation in % | 30 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| Cross Reference Table | | | | |
|-----------------------|----------|----------------|-----------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| 1.4580 | EN | European Union | Tube | |
| 1.458 | DIN | Germany | Steel, Sheet, Plate and Strip | |
| 10216-5 | BS | British | Steel, Sheet, Plate and Strip | |
| X6CrNiMoNb17 12 2 | DIN | Germany | Steel, Sheet, Plate and Strip | |
| X6CrNiMoNb17 12 2 | UNE | Spain | Steel, Bar, Wire, Rod and Forging | |
| X6CrNiMoNb17-12-2 | AFNOR NF | France | Steel, Bar and Rods | |
| 318 S 17 | BS | British | Steel and Wire | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS