



## Material - PN 38 MB 5

## Standard Specification for Mild Steel Alloys Bar and Rod

**Group - Ferrous Mild Steel Alloys** 

Sub Group - PN 38 MB 5 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.360 - 0.420	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	1.150 - 1.450		alizing or Hardoning and
Phosphorus	P %	0.025 max.		
Sulphur	S %	0.035 max.		
Boron	В%	0.0008 - 0.0050		
Iron	Fe %	Balance		
-	-	-		-
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	850 - 1250
-	-	-	Yield Strength in Mpa	700 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardness in HRC	45 max.
-	-	-	Impac <mark>t in Joule</mark>	60 J @ RT

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
38MnB5	EN	European Union	Bar and Rod	
1.5532	EN	European Union	Bar and Rod	
38 MB 5	AFNOR NF	France	Bar, Wire and Rod	
39MnB5	ISO	International	Bar and Rod	
1.5532	NBN	Belgium	Bar and Rod	
38 MB 5	NBN	Belgium	Bar and Rod	
1.5532	PN	Poland	Bar and Rod	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.