

Material - SAE 1006

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets, Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1006 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.080 max.		
Manganese	Mn %	0.250 - 0.400	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Chromium	Cr %	0.070 max.		
Copper	Cu %	0.200 max.		
Molybdenum	Mo %	0.050 max.		
Nickel	Ni %	0.150 max.		
Silicon	Si %	0.200 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	300 - 330
-	-	-	Yield Strength in Mpa	170 min.
-	-	-	Elongation in %	20 min.
-	-	-	Reduction of Area in %	45 - 55
-	-	-	Hardness in HB	86 - 95
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country Grade Belong to the Industry			
G10060	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1006	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
A 1040 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
A 29 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
A 510 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
A 830 1006	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
A 830 G10600	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.