

Material - SAE 1012

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheet and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1012 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.100 - 0.150		
Manganese	Mn %	0.300 - 0.600	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.040 max.		alizing or Hardoning and
Sulphur	S %	0.050 max.		· ·
Chromium	Cr %	0.070 max.		
Copper	Cu %	0.200 max.		
Molybdenum	Mo %	0.050 max.		
Nickel	Ni %	0.150 max.		
Silicon	Si %	0.200 max.	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	330 - 370
-	-	-	Yield Strength in Mpa	180 min.
-	-	-	Elongation in %	19 min.
-	-	-	Reduction of Area in %	40 - 50
-	-	-	Hardness in HB	95 - 105
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10120	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1012	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
A 1040 1012	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
A 29 1012	ASTM	USA	Bar		
A 29 M1012	ASTM	USA	Bar		
A 510 1012	ASTM	USA	Wire Rod		
A 512 Grade 1012	ASTM	USA	Tubing		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.