Material - SAE 1033

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

RAVITY CAST PVT. LTD. RAVITY GROUP OF COMPANIES

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1033Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.360	As Raw or Annealing or Normalizing or Hardening an Tempering	
Manganese	Mn %	0.700 - 1.000		
Phosphorus	Р%	0.030 max.		alizing or Hardoning and
Sulphur	S %	0.035 max.		°
Boron	В%	0.0005 - 0.003		ing .
Copper	Cu %	0.200 min.		
Chromium	Cr %	0.150 max.		
Molybdenum	Mo %	0.060 max.		
Niobium	Nb %	0.200 max.	Mechanical Properties	
Lead	Pb %	0.150 - 0.350	Tensile Strength in Mpa	-
Iron	Fe %	Balance	Yield Strength in Mpa	-
	-	-	Elongation in %	-
	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impa <mark>ct in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
G10330	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1033	AISI	USA	Tubing	
A 1040 1033	ASTM	USA	Steel	
A 513 Grade 1033	ASTM	USA	Steel	
A 830 1033	ASTM	USA	Steel and Plate	
A 830 G10330	ASTM	USA	Steel and Plate	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS