

## Material - SAE 1038

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

**Group - Ferrous Mild Steel Alloys** 

Sub Group - SAE 1038 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 - 0.420		
Manganese	Mn %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Boron	В%	0.0005 - 0.003		
Chromium	Cr %	0.150 max.		
Copper	Cu %	0.200 max.		
Molybdenum	Mo %	0.060 max.		
Nickel	Ni %	0.200 max.	Mechanical Properties	
Lead	Pb %	0.150 - 0.350	Tensile Strength in Mpa	520 - 570
Iron	Fe %	Balance	Yield Strength in Mpa	280 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 - 40
-	-	-	Hardness in HB	149 - 163
-	-	-	Impact in Joule	-

Cross Reference Table					
Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10380	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1038	AISI	USA	Steel and Bar		
A 1040 1038	ASTM	USA	Steel		
A 29 1038	ASTM	USA	Steel and Bar		
A 510 1038	ASTM	USA	Wire Rod and Round Wire		
A 576 10L38	ASTM	USA	Steel and Bar		
A 830 1038	ASTM	USA	Plates and Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.