

Material - SAE 1044

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1044 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.430 - 0.500		
Manganese	Mn %	0.300 - 0.600	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.030 max.		alizing or Hardoning and
Sulphur	S %	0.035 max.		· ·
Boron	В%	0.0005 - 0.003		
Chromium	Cr %	0.150 max.		
Copper	Cu %	0.200 max.		
Molybdenum	Mo %	0.060 max.		
Nickel	Ni %	0.200 max.	Mechanical Properties	
Lead	Pb %	0.150 - 0.350	Tensile Strength in Mpa	550 min.
Iron	Fe %	Balance	Yield Strength in Mpa	300 min.
-	-	-	Elongation in %	16 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in HB	163 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
G10440	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
1044	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing		
M1044	SAE	USA	Steel		
M1044	AISI	USA	Steel		
A 1040 1044	ASTM	USA	Steel		
A 29 1044	ASTM	USA	Steel and Bar		
A 575 M1044	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.