



Material - SAE 1078

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Steel

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1078 Carbon Steel Compositions For Forging To Hot-Rolled Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|----------------|---|-----------|
| Carbon | C % | 0.700 - 0.850 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Manganese | Mn % | 0.300 - 0.600 | | |
| Phosphorus | P % | 0.030 max. | | |
| Sulphur | S % | 0.035 max. | | |
| Boron | B % | 0.0005 - 0.003 | | |
| Chromium | Cr % | 0.150 max. | | |
| Copper | Cu % | 0.200 min. | | |
| Molybdenum | Mo % | 0.060 max. | | |
| Nickel | Ni % | 0.200 max. | | |
| Lead | Pb % | 0.150 - 0.350 | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| | | | Mechanical Properties | |
| | | | Tensile Strength in Mpa | 650 - 690 |
| | | | Yield Strength in Mpa | 380 min. |
| | | | Elongation in % | 10 min. |
| | | | Reduction of Area in % | 30 - 40 |
| | | | Hardness in HB | 192 - 207 |
| | | | Impact in Joule | - |

| Cross Reference Table | | | |
|-----------------------|----------|---------|---|
| Material | Standard | Country | Grade Belong to the Industry |
| G10780 | UNS | USA | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| 1078 | AISI | USA | Steel and Bar |
| A 830 G10780 | ASTM | USA | Plate and Steel |
| A 713 G10780 | ASTM | USA | Steel and Wire |
| A 576 10L78 | ASTM | USA | Steel and Bar |
| A 830 1078 | ASTM | USA | Plate and Steel |
| A 713 Grade 1078 | ASTM | USA | Steel and Wire |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.