



Material - SAE 1524

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1524 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.190 - 0.250	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.350 - 1.650		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.035 max.		
Boron	B %	0.0005 - 0.003		
Chromium	Cr %	0.150 max.		
Copper	Cu %	0.200 max.		
Molybdenum	Mo %	0.060 max.		
Nickel	Ni %	0.200 max.		
Lead	Pb %	0.150 - 1.650		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 510 - 570 Yield Strength in Mpa 280 min. Elongation in % 12 min. Reduction of Area in % 35 - 42 Hardness in HB 149 - 163 Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15240	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1524	AISI	USA	Steel and Bar
A 29 1524	ASTM	USA	Steel and Bar
A 510 1524	ASTM	USA	Wire Rod, Round Wire and Steel
A 830 G15240	ASTM	USA	Plate and Steel
A 513 Grade 1524	ASTM	USA	Tubing
A 519 1524	ASTM	USA	Tubing

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.