

Material - SAE 1552

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE 1552 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|----------------|--|-----------|
| Carbon | C % | 0.470 - 0.550 | | |
| Manganese | Mn % | 1.200 - 1.500 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Phosphorus | P % | 0.030 max. | | |
| Sulphur | S % | 0.035 max. | | |
| Boron | В% | 0.0005 - 0.003 | | |
| Lead | Pb % | 0.150 - 0.350 | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | Mechanical Pro | operties |
| - | - | - | Tensile Strength in Mpa | 680 - 740 |
| - | - | - | Yield Strength in Mpa | 410 min. |
| - | - | - | Elongation in % | 10 min. |
| - | - | - | Reduction of Area in % | 30 - 40 |
| - | - | | Hardness in HB | 193 - 217 |
| - | - | | Impac <mark>t in Joule</mark> | - |

| | Cross Reference Table | | | | |
|--------------|-----------------------|---------|---|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| G15520 | UNS | USA | Bars, Wire Rods, Plates, Strip, Sheets and Tubing | | |
| 1552 | AISI | USA | Steel and Bar | | |
| A 29 1552 | ASTM | USA | Steel and Bar | | |
| A 510 1552 | ASTM | USA | Wire Rod, Round Wire and Steel | | |
| A 830 1552 | ASTM | USA | Plate and Steel | | |
| A 830 G15520 | ASTM | USA | Plate and Steel | | |
| A 866 1552 | ASTM | USA | Steel | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.