



Material - SAE 17-4PH

Standard Specification for Special Purpose Alloys

Group - Ferrous Stainless Steel Alloys

Sub Group - SAE 17-4PH Special Purpose Alloys

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.040 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Chromium	Cr %	15.000 - 17.500		
Nickel	Ni %	3.000 - 5.000		
Niobium	Nb %	0.450 max.		
Copper	Cu %	3.000 - 5.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	861.8 - 1552
-	-	-	Yield Strength in Mpa	620.5 - 1206.6
-	-	-	Elongation in %	3 - 16
-	-	-	Reduction of Area in %	12 min.
-	-	-	Hardness in HB	269 - 510
-	-	-	Impact in Joule	25 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA747 CB7Cu-1	ASME	USA	Casting
J92180	UNS	USA	Casting
Z 7 CNU 17-04	AFNOR NF	France	Steel
5622	AMS	USA	Bar, Wire, Tube and Forging
X 5 CrNiCuNb 16-4	DIN	Germany	Steel
X 5 CrNiCuNb 16-4	EN	European Union	Forging
A747 Grade CB7Cu-1(H900)	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.