

Material - SAE 409

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - SAE 490 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|-----------------|------------------------------------|----------|
| Carbon | C % | 0.080 max. | | |
| Silicon | Si % | 1.000 max. | | |
| Manganese | Mn % | 1.000 max. | | |
| Phosphorus | P % | 0.045 max. | Annealing or Hardening + Tempering | |
| Sulphur | S % | 0.030 max. | | |
| Chromium | Cr % | 10.500 - 11.750 | | |
| Nickel | Ni % | 0.500 max. | | |
| Titanium | Ti % | 0.750 max. | | |
| Iron | Fe % | Balance | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 407 min. |
| - | - | - | Yield Strength in Mpa | 255 min. |
| - | - | - | Elongation in % | - |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in HRC | 68 max. |
| - | - | - | Impac <mark>t in Joule</mark> | - |

| | | _ | | | |
|-----------------------|----------|-----------|-------------------------------|--|--|
| Cross Reference Table | | | | | |
| Material | Standard | Country | Grade Belong to the Industry | | |
| A240 UNS S40900 | ASTM | USA | Steel, Plate, Sheet and Strip | | |
| \$409000 | UNS | USA | Steel | | |
| 409 | AS | Australia | Steel, Sheet, Plate and Strip | | |
| STS 409LTP | KS | Korea | Steel and Pipe | | |
| SUH 409 | JIS | Japan | Steel, Plate and Sheet | | |
| 409 S 19 | BS | British | Steel, Sheet, Plate and Strip | | |
| SA-240 UNS S40900 | ASME | USA | Steel | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.