



Material - SAE 410

Standard Specification for Chemical Compositions Stainless Steels Bar, Wire, Shapes and Forging

Group - Ferrous Stainless Steel Alloys

Sub Group - SAE 410 Chemical Compositions Stainless Steels Bar, Wire, Shapes and Forging

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar, Wire, Shapes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	11.500 - 13.500		
Nickel	Ni %	0.750 max.		
Aluminium	Al %	0.050 max.		
Copper	Cu %	0.500 max.		
Nitrogen	N %	0.080 max.		
Tin	Sn %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-487 Grade CA 15MA	ASME	USA	Casting
J91151	UNS	USA	Casting
SA-487 Grade CA 15M	ASME	USA	Casting
A 487 CA 15M	ASTM	USA	Casting
A217 CA 15	ASTM	USA	Casting
A487 CA 15	ASTM	USA	Casting
A743 CA 15M	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.