

Material - SAE 429

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - SAE 429 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition		Heat Treatment	
C %	0.120 max.		
Si %	1.000 max.		
Mn %	1.000 max.		
P %	0.040 max.	Annealing or Hardening + Tempering	
S %	0.030 max.		
Cr %	14.000 - 16.000		
Fe %	Balance		
-	-		
-	-	Mechanical Pro	operties
-	-	Tensile Strength in Mpa	450 min.
-	-	Yield Strength in Mpa	205 min.
-	-	Elongation in %	22 min.
-	-	Reduction of Area in %	-
-	-	Hardness in HB	183 max.
-	-	Impact in Joule	-
	C % Si % Mn % P % S % Cr % Fe %	C % 0.120 max. Si % 1.000 max. Mn % 1.000 max. P % 0.040 max. S % 0.030 max. Cr % 14.000 - 16.000 Fe % Balance	C % 0.120 max. Si % 1.000 max. Mn % 1.000 max. P % 0.040 max. S % 0.030 max. Cr % 14.000 - 16.000 Fe % Balance - - Fe % Tensile Strength in Mpa Yield Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in HB

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
A240 UNS S42900	ASTM	USA	Steel, Plate, Sheet and Strip	
S42900	UNS	USA	Steel	
STS 429	KS	Korea	Steel, Sheet, Plate and Strip	
SUS 429	JIS	Japan	Steel, Sheet, Plate and Strip	
A182 F429	ASTM	USA	Steel, Pipe and Forging	
A276 429	ASTM	USA	Steel, Bar and Shapes	
A959 Type 429	ASTM	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.