

Material - SAE J403 I SAE J1397 UNS G10150 - Hot Rolled

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G10150 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.130 - 0.180		
Manganese	Mn %	0.300 - 0.600	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	Р%	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	340 min.
-	-	-	Yield Strength in Mpa	190 min.
-	-	-	Elongation in %	28 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardn <mark>ess in HB</mark>	101 max.
	-		Impact in Joule	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
1015	SAE	USA	Steel, Bar, Forging and Tubing	
1015	AISI	USA	Tubing	
A 1040 1015	ASTM	USA	Steel	
A 108 Grade 1015	ASTM	USA	Steel and Bar	
A 29 1015	ASTM	USA	Steel and Bar	
A 29 M1015	ASTM	USA	Steel and Bar	
A 512 Grade 1015	ASTM	USA	Tubing	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.