

Material - SAE J403 I SAE J1397 UNS G10160 - Hot Rolled

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G10160 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|--|--------------------------|
| Carbon | C % | 0.130 - 0.180 | | |
| Manganese | Mn % | 0.600 - 0.900 | | |
| Phosphorus | P % | 0.030 max. | As Paw or Appealing or Normalizing or Hardening an | olizing or Hardoning and |
| Sulphur | S % | 0.050 max. | As Raw or Annealing or Normalizing or Hardening an | |
| Iron | Fe % | Balance | Tempering | iig |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 380 min. |
| - | - | - | Yield Strength in Mpa | 210 min |
| - | - | - | Elongation in % | 25 min. |
| - | - | - | Reduction of Area in % | 50 min. |
| - | - | - | Hardness in HB | 111 max. |
| - | - | | Impact in Joule | - |
| - | | • | | |

| Cross Reference Table | | | | | |
|-----------------------|----------|---------|------------------------------|--|--|
| Material | Standard | Country | Grade Belong to the Industry | | |
| 1016 | SAE | USA | Bars, Wire Rods and Tubing | | |
| 1016 | AISI | USA | Tubing | | |
| A 1040 1016 | ASTM | USA | Steel | | |
| A 108 Grade 1016 | ASTM | USA | Steel and Bar | | |
| A 29 1016 | ASTM | USA | Steel and Bar | | |
| A 510 1016 | ASTM | USA | Wire Rods | | |
| A 512 Grade 1016 | ASTM | USA | Tubing | | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.