

Material - SAE J403 I SAE J1397 UNS G10220 - Cold Drawn

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G10220 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.180 - 0.230		
Manganese	Mn %	0.700 - 1.000		
Phosphorus	Р%	0.030 max.	As Daw or Annualing or Normalizing or Hardoning an	lizing or Hardoning and
Sulphur	S %	0.050 max.	As Raw or Annealing or Normalizing or Hardening an	
Iron	Fe %	Balance	Tempering	ig
-	-	-		
-	-	-		
-	-	-		
-	7	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	480 min.
-	-	-	Yield Strength in Mpa	400 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in HB	137 max.
-	-		Impac <mark>t in Joule</mark>	-
-				

Cross Reference Table				
Material	Standard	Country	Country Grade Belong to the Industry	
1022	SAE	USA	Steel, Bar and Forging	
1022	AISI	USA	Steel, Bar and Forging	
A 1040 1022	ASTM	USA	Steel	
A 108 Grade 1022	ASTM	USA	Steel and Bar	
A 29 1022	ASTM	USA	Steel and Bar	
A 510 1022	ASTM	USA	Wire Rod and Round Wire	
A 513 Grade 1022	ASTM	USA	Tubing	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.