

## Material - SAE J403 I SAE J1397 UNS G10230 - Hot Rolled

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

**Group - Ferrous Mild Steel Alloys** 

Sub Group - SAE J403 I SEA J1397 UNS G10230 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.250		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.030 max.	As Raw or Annealing or Normalizing or Hardening and	
Sulphur	S %	0.050 max.	Tempering	
Iron	Fe %	Balance	rempering	
-	-	-		
-	-	-		
-	-	-		
-	7	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	370 min.
-	-	-	Yield Strength in Mpa	210 min
-	-	-	Elongation in %	25 min.
-	-	-	Reduction of Area in %	50 min.
-	-	-	Hardn <mark>ess in HB</mark>	111 max.
-	-		Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
1023	SAE	USA	Steel		
1023	AISI	USA	Steel and Bar		
A 1040 1023	ASTM	USA	Steel		
A 29 1023	ASTM	USA	Steel and Bar		
A 29 M1023	ASTM	USA	Steel and Bar		
A 510 1023	ASTM	USA	Wire Rod and Round Wire		
A 513 Grade 1023	ASTM	USA	Tubing		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.