

Material - SAE J403 I SAE J1397 UNS G10430 - Cold Drawn

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G10430 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.400 - 0.470		
Manganese	Mn %	0.700 - 1.000	As Raw or Annealing or Normalizing or Hardening and	
Phosphorus	P %	0.030 max.		olizing or Hardoning and
Sulphur	S %	0.050 max.	Tempering	
Iron	Fe %	Balance	rempeniig	
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	630 min.
-	-	-	Yield Strength in Mpa	530 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in HB	179 max.
-	-		Impact in Joule	-
- - - - -			Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in HB	530 min. 12 min. 35 min.

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
1043	SAE	USA	Steel		
1043	AISI	USA	Bar		
A 1040 1043	ASTM	USA	Steel		
A 29 1043	ASTM	USA	Bar		
A 510 1043	ASTM	USA	Wire Rod		
A 576 10L43	ASTM	USA	Steel and Bar		
A 830 1043	ASTM	USA	Plate and Steel		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.