

Material - SAE J403 I SAE J1397 UNS G10500 - Hot Rolled

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G10500 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.550		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	Р%	0.030 max.	As Daw or Annualing or Normalizing or Hardening on	
Sulphur	S %	0.050 max.	As Raw or Annealing or Normalizing or Hardening and	
Iron	Fe %	Balance	Tempering	ıg
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	620 min.
-	-	-	Yield Strength in Mpa	340 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	35 min.
	-	-	Hardn <mark>ess in HB</mark>	179 max.
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
1050	SAE	USA	Steel, Sheet, Strip and Plate		
1050	AISI	USA	Steel, Sheet, Strip and Plate		
A 311 1050 Class A	ASTM	USA	Steel and Bar		
A 311 1050 Class B	ASTM	USA	Steel and Bar		
A 513 Grade 1050	ASTM	USA	Steel and Tubing		
A 684 Grade 1050	ASTM	USA	Steel and Strip		
A 108 Grade 1050	ASTM	USA	Steel and Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.