

Material - SAE J403 I SAE J1397 UNS G10600 - Hot Rolled

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 G10600 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.500 - 0.650		
Manganese	Mn %	0.600 - 0.900	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	Р%	0.030 max.		olizing or Hardoning and
Sulphur	S %	0.050 max.		-
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	680 min.
-	-	-	Yield Strength in Mpa	370 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in BHN	201 max.
-	-		Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
1060	SAE	USA	Steel		
1060	AISI	USA	Steel and Tubing		
A 1040 1060	ASTM	USA	Steel		
A 29 1060	ASTM	USA	Stee and Bar		
A 510 1060	ASTM	USA	Wire Rod, Round Rod and Steel		
A 513 Grade 1060	ASTM	USA	Steel and Tubing		
A 576 10L60	ASTM	USA	Bar		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.