

Material - SAE J403 I SAE J1397 UNS G11170 - Cold Drawn

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G11170 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition		Heat Treatment	
C %	0.140 - 0.200		
Mn %	1.000 - 1.300	As Raw or Annealing or Normalizing or Hardening and Tempering	
Р%	0.030 max.		lizing or Hardoning and
S %	0.080 - 0.130		
Fe %	Balance		
-	-		
-	-		
-	-		
	-	Mechanical Properties	
-	-	Tensile Strength in Mpa	480 min.
-	-	Yield Strength in Mpa	400 min.
-	-	Elongation in %	15 min.
-	-	Reduction of Area in %	40 min.
-	-	Hardness in BHN	137 max.
-	-	Impac <mark>t in Joule</mark>	-
	C % Mn % P % S % Fe %	C % 0.140 - 0.200 Mn % 1.000 - 1.300 P % 0.030 max. S % 0.080 - 0.130 Fe % Balance	C % 0.140 - 0.200 Mn % 1.000 - 1.300 P % 0.030 max. S % 0.080 - 0.130 Fe % Balance - - - - - - - Mechanical Promotion Tensile Strength in Mpa Yield Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in BHN

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1117	SAE	USA	Steel, Bar, Forging and Tubing	
1117	AISI	USA	Steel and Bar	
SUM 31	JIS	Japan	Steel	
A 576 1117	ASTM	USA	Steel and Bar	
SA-311 1117 Class A	ASME	USA	Steel and Bar	
A 576 11L17	ASTM	USA	Steel and Bar	
A 29 1117	ASTM	USA	Steel and Bar	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.