

Material - SAE J403 I SAE J1397 UNS G11410 - Hot Rolled

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G11410 - Hot Rolled Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|--|------------------------|
| Carbon | C % | 0.370 - 0.450 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Manganese | Mn % | 1.350 - 1.650 | | |
| Phosphorus | Р% | 0.030 max. | | izing or Hardoning and |
| Sulphur | S % | 0.080 - 0.130 | | |
| Iron | Fe % | Balance | | 5 |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | 650 min. |
| | - | - | Yield Strength in Mpa | 360 min. |
| | - | - | Elongation in % | 15 min. |
| | - | - | Reduction of Area in % | 35 min. |
| - | - | - | Hardne <mark>ss in BH</mark> N | 187 max. |
| - | - | - | Impac <mark>t in Joule</mark> | - |
| | | | | |

| Cross Reference Table | | | | |
|-----------------------|----------|---------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| 1141 | SAE | USA | Steel | |
| 1141 | AISI | USA | Steel and Bar | |
| A 1040 1141 | ASTM | USA | Steel | |
| A 108 Grade 1141 | ASTM | USA | Steel and Bar | |
| A 29 1141 | ASTM | USA | Steel and Bar | |
| A 311 1141 Class A | ASTM | USA | Steel and Bar | |
| A 311 1141 Class B | ASTM | USA | Steel and Bar | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS