



GRAVITY CAST PVT. LTD.
GRAVITY GROUP OF COMPANIES

Material - SAE J403 | SAE J1397 UNS G11510 - Cold Drawn Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 | SAE J1397 UNS G11510 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.480 - 0.550	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	0.700 - 0.900		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.080 - 0.130		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	700 min.
			Yield Strength in Mpa	590 min.
			Elongation in %	10 min.
			Reduction of Area in %	30 min.
			Hardness in BHN	207 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1151	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1151	AISI	USA	Steel and Bar
A 1040 1151	ASTM	USA	Steel
A 108 Grade 1151	ASTM	USA	Steel and Bar
A 29 1151	ASTM	USA	Steel and Bar
A 510 1151	ASTM	USA	Wire Rod, Round Wire and Steel
A 576 11L51	ASTM	USA	Steel and Bar

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS