

## Material - SAE J403 I SAE J1397 UNS G15240 - Cold Drawn

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

**Group - Ferrous Mild Steel Alloys** 

Sub Group - SAE J403 I SAE J1397 UNS G15240 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.190 - 0.250		
Manganese	Mn %	1.350 - 1.650	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	P %	0.030 max.		lizing or Hardoning and
Sulphur	S %	0.050 max.		•
Iron	Fe %	Balance		ıg
-	-	-		
-	-	-		
-	-	-		
-	7	-	Mechanical Pro	operties
-	-	-	Tensile Strength in Mpa	570 min.
-	-	-	Yield Strength in Mpa	480 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	163 max.
-	-		Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
1524	SAE	USA	Steel		
1524	AISI	USA	Steel and Bar		
A 29 1524	ASTM	USA	Steel and Bar		
A 510 1524	ASTM	USA	Wire Rod, Round Wire and Steel		
A 830 G15240	ASTM	USA	Plate and Steel		
A 513 Grade 1524	ASTM	USA	Tubing		
A 519 1524	ASTM	USA	Tubing		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.