

Material - SAE J403 I SAE J1397 UNS G15410 - Cold Drawn

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 I SAE J1397 UNS G15410 - Cold Drawn Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.360 - 0.440	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.350 - 1.650		
Phosphorus	Р%	0.030 max.		lizing or Hordoning and
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		Ig
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	710 min.
-	-	-	Yield Strength in Mpa	600 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	30 min.
-	-	-	Hardness in BHN	207 max.
-	-	-	Impac <mark>t in Joule</mark>	-
		-		

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1541	SAE	USA	Bars, Plates, Strip, Sheets, Tubing and Forging	
1541	AISI	USA	Bar and Steel	
A 29 1541	ASTM	USA	Bar and Steel	
A 311 1541 Class A	ASTM	USA	Bar and Steel	
A 311 1541 Class B	ASTM	USA	Bar and Steel	
A 830 G15410	ASTM	USA	Plate and Steel	
A 510 1541	ASTM	USA	Wire Rod, Round Wire and Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

ONE STOP SOLUTION FOR METAL PARTS