

## Material - SAE J403 UNS G10130

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

**Group - Ferrous Mild Steel Alloys** 

Sub Group - SAE J403 UNS G10130 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.110 - 0.160		
Manganese	Mn %	0.300 - 0.600	As Raw or Annealing or Normalizing or Hardening and Tempering	
Phosphorus	Р%	0.030 max.		zing or Hardoning and
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		5
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardn <mark>ess in HB</mark>	-
-	-	-	Impac <mark>t in Joule</mark>	-
7		-		

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
1013	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
1013	AISI	USA	Bar	
A 1040 1013	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	
A 29 1013	ASTM	USA	Bar	
A 510 1013	ASTM	USA	Wire Rod	
SA-29 1013	ASME	USA	Bar	
K11430	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing	

## Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.

## ONE STOP SOLUTION FOR METAL PARTS