

Material - SAE J403 UNS G10750

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 UNS G10750 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.700 - 0.800		
Manganese	Mn %	0.400 - 0.700	As Raw or Annealing or Normalizing or Hardening an Tempering	
Phosphorus	P %	0.030 max.		alizing or Hardoning and
Sulphur	S %	0.050 max.		•
Iron	Fe %	Balance		ing
-	-	-		
-	-	-		
-	-	-		
-	-	-	Mechanical P	roperties
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	
-	-	-	Impact in Joule	-

Cross Reference Table				
Material	Standard	Country	Grade Belong to the Industry	
1075	SAE	USA	Steel	
1075	AISI	USA	Steel and Bar	
A 1040 1075	ASTM	USA	Steel	
A 29 1075	ASTM	USA	Steel and Bar	
A 510 1075	ASTM	USA	Steel	
A 713 G10750	ASTM	USA	Steel	
A 713 Grade 1075	ASTM	USA	Steel	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.