

Material - SAE J403 UNS G15260

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 UNS G15260 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment	
Carbon	C %	0.220 - 0.290	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.100 - 1.140		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	7	-	Mechanical P	roperties
-	-	-	Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-		Impact in Joule	-
- - - - - -	-		Tensile Strength in Mpa Yield Strength in Mpa Elongation in % Reduction of Area in % Hardness in BHN	roperties

Cross Reference Table						
Material	Standard	Country	Grade Belong to the Industry			
1526	SAE	USA	Bar, Plate, Strip, Sheets and Tubing			
1526	AISI	USA	Bar, Plate, Strip, Sheets and Tubing			
A 29 1526	ASTM	USA	Bar			
A 510 1526	ASTM	USA	Steel			
A 576 15L26	ASTM	USA	Steel and bar			
-	-	-	-			
-	-	-	-			

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.