



Material - SAE J403 UNS G15470

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets and Tubing

Group - Ferrous Mild Steel Alloys

Sub Group - SAE J403 UNS G15470 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bars, Wire Rods, Plates, Strip, Sheets and Tubing

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|---|---|
| Carbon | C % | 0.430 - 0.510 | As Raw or Annealing or Normalizing or Hardening and Tempering | |
| Manganese | Mn % | 1.350 - 1.650 | | |
| Phosphorus | P % | 0.030 max. | | |
| Sulphur | S % | 0.050 max. | | |
| Iron | Fe % | Balance | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| - | - | - | | |
| | | | Mechanical Properties | |
| - | - | - | Tensile Strength in Mpa | - |
| - | - | - | Yield Strength in Mpa | - |
| - | - | - | Elongation in % | - |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in BHN | - |
| - | - | - | Impact in Joule | - |

| Cross Reference Table | | | |
|-----------------------|----------|---------|---|
| Material | Standard | Country | Grade Belong to the Industry |
| 1547 | SAE | USA | Bars, Wire Rods, Plates, Strip, Sheets and Tubing |
| 1547 | SAE | USA | Bar and Steel |
| SMnC443 | JIS | Japan | Steel |
| NV 2 | SAE | USA | Valve |
| SMnC443 | SAE | USA | Valve |
| A 576 15L47 | ASTM | USA | Steel and Bar |
| A 510 1547 | ASTM | USA | Wire Rod, Round Wire and Steel |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.