



**GRAVITY CAST PVT. LTD.**  
**GRAVITY GROUP OF COMPANIES**

## Material - SAE NV 2

**Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Valve**

**Group - Ferrous Mild Steel Alloys**

**Sub Group - SAE NV 2 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Valve**

**Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries**

**Grade Belongs to the Industry - Valve**

Chemical Composition			Heat Treatment	
Carbon	C %	0.430 - 0.510	As Raw or Annealing or Normalizing or Hardening and Tempering	
Manganese	Mn %	1.350 - 1.650		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	1240 min.
			Yield Strength in Mpa	1140 min.
			Elongation in %	15 min.
			Reduction of Area in %	40 min.
			Hardness in HRC	40 max.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G15470	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1547	SAE	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1547	SAE	USA	Bar and Steel
SMnC443	JIS	Japan	Steel
SMnC443	SAE	USA	Valve
A 576 15L47	ASTM	USA	Steel and Bar
A 510 1547	ASTM	USA	Wire Rod, Round Wire and Steel

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.