



## Material - SS 1.6220

### Standard Specification for Steel Castings for General Engineering Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - SS 1.6220 Steel Castings for General Engineering Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.170 - 0.230	As Cast or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.000 - 1.600		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.150 max.		
Nickel	Ni %	0.800 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance	<b>Mechanical Properties</b> Tensile Strength in Mpa      480 - 650 Yield Strength in Mpa      300 min. Elongation in %      20 min. Reduction of Area in %      - Hardness in BHN      - Impact in Joule      50 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AM2	BS	British	Casting
2074/C3	AS	Australia	Casting
1.622	ONORM	Australia	Casting
1.622	EN	European Union	Casting
1.622	BDS	Bulgaria	Casting
1.622	DIN	Germany	Casting
1.622	UNE	Spain	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.