



Material - SS 1606

Standard Specification for High Carbon Cast Steel

Group - Ferrous Mild Steel Alloys

Sub Group - SS 1606 High Carbon Cast Steel

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.500 max.	Annealing or Normalising or Hardening + Tempering	
Silicon	Si %	0.500 max.		
Manganese	Mn %	0.700 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties Tensile Strength in Mpa 621 min. Yield Strength in Mpa 345 min. Elongation in % 20 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1050.0000	AISI	USA	Forging, Bar, Wire, and Shape
50 CD 4-M	AFNOR NF	France	Casting
5152	SAE	USA	Steel
735 A 51	BS	British	Hot Formed Spring
C 3	MSZ	Hungary	Steel
C48GW-N-A	JIS	Japan	Forging
A732 4A	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.