



Material - SS 2304

Standard Specification for Stainless Steel - SS Steel 23 04

Group - Ferrous Stainless Steel Alloys

Sub Group - SS 2304 Stainless Steel - SS Steel 23 04

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar, Wire, Shapes and Forging

Chemical Composition			Heat Treatment	
Carbon	C %	0.260 - 0.350	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	12.000 - 14.000		
Nickel	Ni %	1.000 max.		
Iron	Fe %	Balance		
-	-	-		
Mechanical Properties				
Tensile Strength in Mpa		690 min.		
Yield Strength in Mpa		485 min.		
Elongation in %		15 min.		
Reduction of Area in %		25 min.		
Hardness in HB		269 max.		
Impact in Joule		-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4028	EN	European Union	Forging
SUS 420J2	JIS	Japan	Forging
30CH13	GOST	Russia	Bar, Wire, Shapes and Forging
420	AISI	USA	Bar, Wire, Shapes and Forging
X 30Cr13	UNI	Italy	Bar, Wire, Shapes and Forging
420 S 45	BS	British	Bar, Wire, Shapes and Forging
A743 CA20	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.