



Material - STAS 10 CrMo 10

Standard Specification for Steel for Boiler Tubes

Group - Ferrous Mild Steel Alloys

Sub Group - STAS 10 CrMo 10 Steel for Boiler Tubes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Tube

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.150 - 0.500		
Manganese	Mn %	0.400 - 0.700		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Chromium	Cr %	2.000 - 2.500		
Nickel	Ni %	0.300 max.		
Molybdenum	Mo %	0.900 - 1.100		
Titanium	Ti %	0.020 max.	Mechanical Properties	
Arsenic	As %	0.050 max.	Tensile Strength in Mpa	585 min.
Copper	Cu %	0.300 max.	Yield Strength in Mpa	380 min.
Iron	Fe %	Balance	Elongation in %	20 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.7375	DIN	Germany	Tube
1.7380	EN	European Union	Bar, Plate and Forging
10 CD 9-10	AFNOR NF	France	Plate
J22090	UNS	USA	Casting
10 CrMo 9-10	MSZ	Hungary	Bar, Tube and Forging
10 CrMo 9-10	BS	British	Steel
A356 10	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.