



## Material - STAS 16 Mo 3

## **Standard Specification for Seemless Steel Tubes for Pressure Purposes**

**Group - Ferrous Mild Steel Alloys** 

Sub Group - STAS 16 Mo 3 Seemless Steel Tubes for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry - Steel and Plates** 

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 - 0.200		
Silicon	Si %	0.150 - 0.350		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.035 max.	Normalising Forming	
Sulphur	S %	0.030 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.250 - 0.400		
Nickel	Ni %	0.300 max.		•
Aluminium	Al %	0.010 - 0.030	Mechanical Properties	
Arsenic	As %	0.070 max.	Tensile Strength in Mpa	-
Iron	Fe %	Balance	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-		Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table					
Material	Standard	Country	Grade Belong to the Industry		
1.5415	EN	European Union	Tube		
16 Mo 3	AFNOR NF	France	Steel and Tube		
16 Mo 3	BS	British	Steel and Tube		
16 Mo 3	DIN	Germany	Steel and Tube		
16 Mo 3	ISO	International	Steel, Forging, Rolling and Bar		
16 Mo 3	NBN	Belgium	Steel and Tube		
16 Mo 3	UNI	Italy	Steel and Tube		

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.