

Material - STAS 2 CuMoCrNi 250

Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

Group - Ferrous Stainless Steel Alloys

Sub Group - STAS 2 CuMoCrNi 250 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade Belongs to the Industry - Steel

Chemical Composition			Heat Treatment	
Carbon	C %	0.020 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	2.000 max.	Solution Annealing	
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.025 max.		
Chromium	Cr %	19.000 - 22.000		
Molybdenum	Mo %	4.000 - 5.000		
Nickel	Ni %	24.000 - 27.000		_
Copper	Cu %	1.000 - 2.000	Mechanical Properties	
Iron	Fe %	Balance	Tensile Strength in Mpa	490 min.
-	-	-	Yield Strength in Mpa	215 min.
-	-	-	Elongation in %	35 min.
-	-	-	Reduction of Area in %	40 min.
-	-	-	Hardness in HB	187 max.
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table					
Material	Standard	Country Grade Belong to the Industry			
A240 UNS N08904	ASTM	USA	Steel, Plate, Sheet and Strip		
SUS 890L	JIS	Japan	Steel, Plate, Sheet and Strip		
TU Z 1 NCDU 25 20 04	AFNOR NF	France	Steel and Tube		
X1NiCrMoCu25 20 5	EN	European Union	Forging		
X1NiCrMoCu25-20-5	UNI	Italy	Steel, Plate, Sheet and Strip		
X1NiCrMoCu25 20 5	DIN	Germany	Rolling and Forging		
STS 890L	KS	Korea Steel, Plate, Sheet and Strip			

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.