



Material - STAS T 100 MoMn 130

Standard Specification for Austenitic Manganese Steel Casting

Group - Ferrous Austenitic Manganese Steel Alloy
Sub Group - STAS T 100 MoMn 130 Austenitic Manganese Steel Casting
Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries
Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	С%	0.700 - 1.300		
Silicon	Si %	1.000 max.		
Manganese	Mn %	11.500 - 14.000	Annealing or Normalising or Hardening + Tempering	
Phosphorus	P %	0.070 max.		Hardening + Tempering
Sulphur	S %	0.050 max.		
Molybdenum	Mo %	0.900 - 1.200		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-		Tensile Strength in Mpa	-
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-		Hardn <mark>ess in BH</mark> N	
-	-	-	Impac <mark>t in Joule</mark>	-

Cross Reference Table				
Material	Standard	Country Grade Belong to the Industry		
J91249	UNS	USA	Casting	
A128 Grade E-1	ASTM	USA	Casting	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	
-	-	-	-	

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.