



Material - UNE F.1201

Standard Specification for Mild Steel Alloys Bar and Rod

Group - Ferrous Mild Steel Alloys

Sub Group - UNE F.1201 Mild Steel Alloys Bar and Rod

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.340 - 0.410	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.900 - 1.200		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 750 - 900 Yield Strength in Mpa 510 min. Elongation in % 14 - 40 Reduction of Area in % - Hardness in BHN As Per HT Impact in Joule 35 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
37Cr4	EN	European Union	Bar and Rod
1.7034	EN	European Union	Bar and Rod
37CrS4	EN	European Union	Bar and Rod
1.7038	EN	European Union	Bar and Rod
34 Cr 4 E	ISO	International	Bar and Rod
34 Cr 4 E	JIS	Japan	Bar and Rod
Cr 2 Z	MSZ	Hungary	Bar and Rod

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.