



Material - UNE F.8375

Standard Specification for Ferritic Casting Steels for Low Temperatures

Group - Ferrous Mild Steel Alloys

Sub Group - UNE F.8375 Ferritic Casting Steels for Low Temperatures

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 max.	Normalising + Tempering or Hardening + Tempering	
Silicon	Si %	0.300 - 0.600		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Nickel	Ni %	4.000 - 5.000		
Iron	Fe %	Balance		
-	-	-		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	485 - 655
-	-	-	Yield Strength in Mpa	275 min.
-	-	-	Elongation in %	24 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-352 Grade LC4	ASME	USA	Casting
AM8Ni18	UNE	Spain	Casting
J14501	UNS	USA	Casting
J14500	UNS	USA	Casting
A575 B4N B4Q	ASTM	USA	Casting
A352 LC4	ASTM	USA	Casting
-	-	-	-

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.