



Material - UNE GP 240 GH

Standard Specification for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - UNE GP 240 GH Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Plate, Tubes and Forging

| Chemical Composition | | | Heat Treatment | |
|----------------------|------|---------------|--|-----------|
| Carbon | C % | 0.180 - 0.230 | | |
| Silicon | Si % | 0.600 max. | Normalizing or Quenching or Solution Annealing | |
| Manganese | Mn % | 0.500 - 1.200 | | |
| Phosphorus | P % | 0.300 max. | | |
| Sulphur | S % | 0.020 max. | | |
| Chromium | Cr % | 0.300 max. | | |
| Molybdenum | Mo % | 0.120 max. | | |
| Nickel | Ni % | 0.400 max. | | |
| Copper | Cu % | 0.300 max. | Mechanical Properties | |
| Vanadium | V % | 0.030 max. | Tensile Strength in Mpa | 420 - 600 |
| Iron | Fe % | Balance | Yield Strength in Mpa | 240 min. |
| - | - | - | Elongation in % | 22 min. |
| - | - | - | Reduction of Area in % | - |
| - | - | - | Hardness in HB | - |
| - | - | - | Impac <mark>t in Joule</mark> | 27 J @ RT |

| Cross Reference Table | | | | |
|-----------------------|----------|----------------|------------------------------|--|
| Material | Standard | Country | Grade Belong to the Industry | |
| EN 10213 GP240GH | BS | British | Plate, Tubes and Forging | |
| A 216 Grade WCB | ASTM | USA | Casting | |
| A 420 C-M | AFNOR NF | France | Pump, Valve and Fitting | |
| A 420 M | AFNOR NF | France | Pump, Valve and Fitting | |
| Ao 17 CrMoV | MSZ | Hungary | Plate, Tubes and Forging | |
| SCPH 1 | JIS | Japan | Plate, Tubes and Forging | |
| 1.0619 | EN | European Union | Plate, Tubes and Forging | |

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.