



## Material - UNI G 17 CrMoV 5-10

### Standard Specification for Technical Delivery Conditions for Steel Castings for Pressure Purposes

Group - Ferrous Mild Steel Alloys

Sub Group - UNI G 17 CrMoV 5-10 Technical Delivery Conditions for Steel Castings for Pressure Purposes

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.200	Normalising or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.900		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	1.200 - 1.500		
Molybdenum	Mo %	0.900 - 1.100		
Nickel	Ni %	0.400 max.		
Vanadium	V %	0.200 - 0.300		
Copper	Cu %	0.300 max.		
Tin	Sn %	0.025 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
422744	CSN	Czech Republic	Casting
1.7706	EN	European Union	Casting
1.7706	DIN	Germany	Casting
G 17 CrMoV 5-10	AFNOR NF	France	Casting
J21610	UNS	USA	Casting
L 17 HMF	PN	Poland	Casting
A356 9	ASTM	USA	Casting

**Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email [marketing@gravitycastindia.com](mailto:marketing@gravitycastindia.com)**

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.