



Material - UNI G X 40 CrNi 26-20

Standard Specification for Austenitic Stainless Steel Heat Resisting Steel and Alloy Sand Castings

Group - Ferrous Stainless Steel Alloys

Sub Group - UNI G X 40 CrNi 26-20 Austenitic Stainless Steel Heat Resisting Steel and Alloy Sand Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry - Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.600	As - Cast	
Silicon	Si %	2.500 max.		
Manganese	Mn %	2.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	24.000 - 28.000		
Nickel	Ni %	18.000 - 22.000		
Molybdenum	Mo %	0.500 max.		
Iron	Fe %	Balance		
-	-	-		
			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	440 min.
-	-	-	Yield Strength in Mpa	240 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
310C40	BS	British	Casting
1.4848	DIN	Germany	Casting
J94224	UNS	USA	Casting
422952	CSN	Czech Republic	Casting
40 CrNiSi 25-20	MSZ	Hungary	Casting
393 G X 40 CrNi 25-20	SFS	Finland	Casting
A297 Grade HK	ASTM	USA	Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business.